



**TECHNICAL DATA SHEET**

# 416NMN212 - 416 Nomex® / PET / 416 Nomex®

## Class H 180°C Insulation

A composite laminate of type 416 Nomex® meta-aramid fiber sandwiched between two electrical grade PET polyester films, bonded by a high temperature structural adhesive system.

### PRODUCT ATTRIBUTES

- Excellent thermal stability and electrical properties
- High tear, tensile, and burst strength
- Excellent moisture and chemical resistance
- UL 1446 220°C and recognized insulation system, file E60273

### PRODUCT APPLICATIONS

- Flexible circuit materials
- Power distribution
- Heating elements
- Electrical cables

REPRESENTATIVE PHYSICAL PROPERTIES		
PROPERTY	VALUE	TEST METHOD
<b>NOMINAL THICKNESS</b> , inches	0.005	ASTM D374
<b>YIELD</b>		
Square yards per pound	3.96	
Pounds per Square Yards	0.25	
<b>DIELECTRIC STRENGTH</b> (Volts – 2" electrodes)	7,700	ASTM D149
<b>DIELECTRIC CONSTANT</b> (23°C, 50% RH, 60 Hz)	3.2	ASTM D150
<b>DISSIPATION FACTOR</b> (23°C, 50% RH, 60 Hz)	0.005	ASTM D150
<b>VOLUME RESISTIVITY</b> (Ohm-cm) (23°C, 50% RH)	10 <sup>15</sup>	ASTM 257-66
<b>SURFACE RESISTIVITY</b> (Ohm) (23°C, 50% RH)	10 <sup>15</sup>	ASTM-257-66

### STORAGE

- Shelf life: one (1) year
- Store in a clean area free from exposure to excessive heat, moisture or direct sunlight (50°F to 80°F).

*Product performance will vary in each application and is dependent upon composite construction. Arlon Innovations does not guarantee the replication of this data by third parties. None of the data or statements contained herein is intended to warrant the performance of this product. Data is representative and not intended as a manufacturing specification.*