

Arlon Innovations210.798.19006110 Rittiman Road800.549.9860San Antonio, TX 78218arloninnovations.com

## **TECHNICAL DATA SHEET**

# 416NMN222 - 416 Nomex<sup>®</sup> / PET / 416 Nomex<sup>®</sup> Class H 180°C Insulation

A composite laminate of type 416 Nomex<sup>®</sup> meta-aramid fiber sandwiched between two electrical grade PET polyester films, bonded by a high temperature structural adhesive system.

# **PRODUCT ATTRIBUTES**

- Excellent thermal stability and electrical properties
- High tear, tensile, and burst strength
- Excellent moisture and chemical resistance
- UL 1446 220°C and recognized insulation system, file E60273

#### **PRODUCT APPLICATIONS**

- Flexible circuit materials
- Power distribution
- Heating elements
- Electrical cables

REPRESENTATIVE PHYSICAL PROPERTIES		
PROPERTY	VALUE	TEST METHOD
NOMINAL THICKNESS, inches	0.006	ASTM D374
YIELD		
Square yards per pound	3.08	
Pounds per Square Yards	0.32	
DIELECTRIC STRENGTH		
(Volts – 2" electrodes)	11,000	ASTM D149
DIELECTRIC CONSTANT		
(23°C, 50% RH, 60 Hz)	3.2	ASTM D150
TENSILE STRENGTH (psi)		
Machine Direction (MD)	95	ASTM D828
Cross Machine Direction (XMD)	70	
GRAVES TEAR STRENGTH (lbs)		
Machine Direction (MD)	9	ASTM D1004
Cross Machine Direction (XMD)	7	
DISSIPATION FACTOR	0.005	ASTM D150
(23°C, 50% RH, 60 Hz)	0.005	ASTM DISO
VOLUME RESISTIVITY (Ohm-cm)	1015	ASTM 257-66
(23°C, 50% RH)		ASTM 237-00
SURFACE RESISTIVITY (Ohm)	1015	ASTM-257-66
(23°C, 50% RH)		ASTN-237-00

## STORAGE

- Shelf life: one (1) year
- Store in a clean area free from exposure to excessive heat, moisture or direct sunlight (50°F to 80°F).

Product performance will vary in each application and is dependent upon composite construction. Arlon Innovations does not guarantee the replication of this data by third parties. None of the data or statements contained herein is intended to warrant the performance of this product. Data is representative and not intended as a manufacturing specification.